

Polymers

SABIC[®] EPDM 626

Ethylene Propylene Diene Rubber

Revision Date: May 2016

PRODUCT DESCRIPTION:

EPDM 626 is a high ethylene and low ENB grade produced by solution polymerization using metallocene catalyst. It has a tailored molecular weight distribution. This product is available in pellet form.

CHARACTERISTICS:

Compared to typical narrow MWD grades EPDM 626 is designed for:

- Better physical properties
- Improved mixing and mill handling
- Improved calenderability
- Better oil retention
- Reduced cure bloom in compounds

TYPICAL APPLICATIONS:

- Sheeting goods
- Roofing membranes and water proofing systems

TYPICAL DATA:

PROPERTIES	Unit	Typical Value ⁽¹⁾	Test Method
Mooney Viscosity (ML 1+4, 125°C)	MU	67	ASTM-D 1646
Ethylene Content	Wt%	69	ASTM-D 3900
Ethylidene Norbornene (ENB) Content	Wt%	2.8	ASTM-D 6047

(1) Typical values; not to be construed as specification limits.

STORAGE:

EPDM 626 should be stored in its original packing at ambient temperature in dry conditions; flow ability of the pellets can be negatively influenced by pressure or high temperature; exposure to ultraviolet light and direct sun light has to be avoided. SABIC will not extend its warranty when storage conditions are inadequate which may lead to quality deterioration such as color change that could result in inadequate product performance.

For additional technical, sales and order assistance:

Middle East, Africa, & India Subcontinent

SABIC (HQ)
PO Box 5101,
Riyadh 11422,
Saudi Arabia
T +966 (0) 11 225 8000
F +966 (0) 11 225 9000
E info@sabic.com

Europe

SABIC Europe
PO Box 5151,
6130 PD Sittard,
The Netherlands
T +31 467 222 222
F +31 467 220 000
E info@sabic-europe.com

Asia Pacific

SABIC Asia Pacific Pte. Ltd.
One Temasek Avenue,
06-01 Millenia Tower,
Singapore 039192
T +65 655 725 55
F +65 653 181 01
E sappl@sabic.com.sg

United States

SABIC Americas, Inc.
2500 City West Boulevard,
Suite 650, Houston,
TX 77042, USA
T +1 713 532 4999
F +1 713 532 4994
E info@americas.sabic.com

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.